

Pigments

Pigments for
Coatings



SUDARSHAN

First Choice For New Formulations

Pigments

For Coatings

	Product Name & Code	C. I. Name	Decorative Paints		Industrial Coatings					Light fastness Full Tone/Tint	Weather fastness Full Tone/Tint	Heat Stability (°C)	Overspray
			Solvent Base	Water Base	Automotive OEM	Automotive Refinish	Industrial Paints	Powder Coatings	Coil Coatings				
	Sudaperm™ Yellow 2903	PY 151	●		○	●	●	●		8/7	5/4	180	5
	Sudaperm™ Yellow 2906	PY 154	●	●	○	●	●	●		8/7	5/4	160	5
	Sudacolor™ Yellow G	PY 1	●	●						7/5			
	Sudafast™ Yellow 127	PY 74	●	●			○			7/5	4/2		
	Sudafast™ Yellow 117	PY 74	●	●						7/5	4/2		
	Sudafast™ Yellow 128C	PY 74	○	●						6/5	4/2		
	Sudacolor™ Yellow 118	PY 65	●	●						6/5	4/2		3
	Sudacolor™ Yellow 119C	PY 65	●	●						6/5	4/2		3
	Sudafast™ Yellow 134	PY 83	●	●			●	●		7/6	4/3	200	4-5
	Sudafast™ Yellow 137C	PY 83	●	○			●	●		7/5		200	
	Sudaperm™ Yellow 2935	PY 139	●		○	●	●	●		7-8/7	4/3-4	180	5
	Sudaperm™ Yellow 2929C	PY 110	○	●	●	●	●	●	○	8/7	5/4	200	5
	Sudaperm™ Yellow 2926C	PY 110	○	●	●	●	●	●	○	8/7	5/4	180	4-5
	Sudaperm™ Orange 2919	PO 64						●	○	5-6/3		180	
	Sudaperm™ Orange 2915C	PO 36	●	●	○	●	●	●		8/7	5/4	160	5
	Sudacolor™ Red 401	PR 4	●	●						6/3			
	Sudacolor™ Red 417	PR 3	●	●						6/4			
	Sudacolor™ Red 415	PR 3	●	○						6/4			
	Sudafast™ Red 341	PR 112	●	●						7-8/6			
	Sudafast™ Red 336	PR 112	●	●						7/6			
	Sudafast™ Red 331	PR 112	●	●						7/5-6			
	Sudaperm™ Red 2964C	PR 170	●	●		○	●	●		7/5	4/2	180	4-5
	Sudaperm™ Red 2963C	PR 170	●	●		●	●	●		7/5	4/2	180	4-5
	Sudaperm™ Red 2967C	PR 170	●	●		●	●	●		7/5	4/2	180	4-5
	Sudaperm™ Red 2951C	PR 264		○	●	●	●	●	○	8/8	5/5	200	5
	Sudaperm™ Red 2953C	PR 264			●	●	●	●	○	8/7	5/4	200	4-5
	Sudaperm™ Red 2975C	PR 177			●	●	●	●	○	7-8/7	5/4	200	5
	Sudaperm™ Red 2987	PV 19	●	●	○	●	●	●	●	8/7	5/4	200	5
	Sudaperm™ Pink 2998	PR 122	○	●						8/7	5/4	200	5

Note: Light fastness is assessed on 1-8 Blue Wool Scale where 1= Poor & 8 = Excellent
Weather fastness is assessed on 1-5 Grey Scale where 1= Poor & 5= Excellent

● Suitable for application ○ Potential Use




Pigments

For Coatings

Product Name & Code	C. I. Name	Decorative Paints		Industrial Coatings					Light fastness Full Tone/Tint	Weather fastness Full Tone/Tint	Heat Stability (°C)	Overspray
		Solvent Base	Water Base	Automotive OEM	Automotive Refinish	Industrial Paints	Powder Coatings	Coil Coatings				
Sudaperm™ Pink 2999	PR 122	○	●						8/7	5/4	200	5
Sudaperm™ Pink 2997C	PR 122	●	●	●	●	●	●	●	8/7	5/4	200	5
Sudaperm™ Red Violet 2996	PV 19	○	●	●	●	●	●	●	8/7	5/4	200	5
Sudaperm™ Red Violet 2995	PV 19	○	●	●	●	●	●	●	8/7	5/4	200	5
Sudafast™ Blue 2662	PB 15:1	●	●		○	●	○	●	8/8	5/5	200	5
Sudafast™ Blue 2764	PB 15:1						●		8/8	5/5	200	5
Sudafast™ Blue 2773	PB 15:2	○	●	●	●	●	○	●	8/8	5/5	200	5
Sudafast™ Blue 2774	PB 15:2	○	●	●	●	●	○	●	8/8	5/5	200	5
Sudafast™ Blue 2778C	PB 15:3	●	●			○	○	○	8/8	5/5	200	5
Sudafast™ Blue 2784	PB 15:3	●	●		○	●	○	●	8/8	5/5	200	5
Sudafast™ Blue 2785	PB 15:3	●	●						8/8		200	5
Sudafast™ Blue 2789	PB 15:3						●		8/8	5/5	200	5
Sudafast™ Blue 2796	PB 15:4	●	●	●	●	●	○	●	8/8	5/5	200	5
Sudafast™ Green 2727C	PG 7	●	●	○	●	●	●	●	8/8	5/5	200	5

● Suitable for application ○ Potential Use




Sudaperm™
Yellow 2903 PY151

Sudaperm™
Yellow 2906 PY154

Sudacolor™
Yellow G PY1

Sudafast™
Yellow 127 PY74

Sudafast™
Yellow 117 PY74




Sudafast™
Yellow 128C PY74

Sudacolor™
Yellow 118 PY65

Sudacolor™
Yellow 119C PY65

Sudafast™
Yellow 134 PY83

Sudafast™
Yellow 137C PY83



Sudaperm™
Yellow 2935 PY139

Sudaperm™
Yellow 2929C PY110


Sudaperm™
Yellow 2926C PY110

Sudaperm™
Orange 2919 P064

Sudaperm™
Orange 2915C P036

Pigments

For Coatings




Sudacolor™
Red 401 PR4

Sudacolor™
Red 417 PR3

Sudacolor™
Red 415 PR3

Sudafast™
Red 341 PR112

Sudafast™
Red 336 PR112




Sudafast™
Red 331 PR112

Sudaperm™
Red 2964C PR170

Sudaperm™
Red 2963C PR170

Sudaperm™
Red 2967C PR170

Sudaperm™
Red 2951C PR264




Sudaperm™
Red 2953C PR264

Sudaperm™
Red 2975C PR177

Sudaperm™
Red 2987 PV19

Sudaperm™
Pink 2998 PR122

Sudaperm™
Pink 2999 PR122



Sudaperm™
Pink 2997C PR122

Sudaperm™
Red Violet 2996 PV19

Sudaperm™
Red Violet 2995 PV19

Sudafast™
Blue 2662 PB15:1

Sudafast™
Blue 2764 PB15:1



Sudafast™
Blue 2773 PB15:2

Sudafast™
Blue 2774 PB15:2

Sudafast™
Blue 2778C PB15:3

Sudafast™
Blue 2784 PB15:3

Sudafast™
Blue 2785 PB15:3



Sudafast™
Blue 2789 PB15:3

Sudafast™
Blue 2796 PB15:4

Sudafast™
Green 2727C PG7

Color Reproduction: For technical reasons connected with color reproduction, the colors shown may not exactly match the pigment colors and do not represent a particular finish.

Tint shades are reproduced with a ratio of Pigment: TiO₂ = 1:10.

Light fastness is assessed on 1-8 Blue Wool Scale where 1= Poor & 8 = Excellent

Weather fastness is assessed on 1-5 Gray Scale where 1= Poor & 5= Excellent

Why Us?



About Us

Sudarshan is a leading global producer of performance colorants, manufacturing an extensive range of Organic, Inorganic and Pearlescent pigments as well as Dispersions.

Sudarshan's quality pigments and dispersions add outstanding performance, long term protection, brilliant color and special effect to the Coatings, Plastics, Printing Ink, Cosmetics, Paper and Textile industries.

Sudarshan has over 60 years of manufacturing experience, with sales in more than 85 countries and sales presence in North America, Europe, China and Latin America.

Technical Capability, Infrastructure and Commitment to Quality

Our commitment to being a world class solution provider is maintained by our technical capabilities and an infrastructure that supports the wide customer base that we cater to.

This capability is a combination of a comprehensive gate-review process in product development; state-of-the-art analytical testing facilities that enable a wide range of investigative methods and a data driven approach; and an application lab that accurately recreates the behavior of our product in our customer's application to provide the optimal solution.

Each year, we invest substantially in R&D and Applications Service to support our customers technically and to extend our range of products to meet our customers' requirements.

Our quality, environment and safety systems are based on and accredited with international standards. Our improvement programs are being driven through 6-sigma methodology.



Ecological & Toxicological Association of Dyes & Organic pigment manufacturers



ISO 9001

ISO 17025

ISO 14001

Pigments

Contact Us

Sudarshan Chemical Industries Limited

Global Head Office:
162 Wellesley Road
Pune - 411 001, India
Tel: +91 20 260 58 888
Fax: +91 20 260 58 222
Email: contact@sudarshan.com

Sudarshan Europe B.V.

Kingsfordweg 151
1043 GR Amsterdam
Tel: +31 (0)20 491 9417
Fax: +31 (0)20 491 9415
Email: eu@sudarshan.com

Sudarshan North America Inc.

76 N. Walnut Street
Ridgewood, NJ
USA 07450
Tel: +1 201 300 2770
Email: usa@sudarshan.com

Sudarshan (Shanghai) Trading Company Limited

Room 1911, 19/F New Hualian Mansion,
East Wing, No. 755 Middle Huaihai Road,
Huangpu District, Shanghai, China, 200020
Tel: +86 21 2215 7500, +86 21 2215 7559
Fax: +86 21 2215 7463
Email: china@sudarshan.com

Sudarshan Mexico S. de R.L. de CV.

Av. Chalma s/n Oficina b-13
Jardines de la Hacienda Sur, 54720
Cuautitlan Izcalli, Edo. de Mexico, Mexico
Tel: +52 55 2472 0246
Email: mexico@sudarshan.com



www.sudarshan.com